

On the problem of Yb_4As_3 .

M S. Laad and J.R. Reyes Martinez¹

¹*Institut für Theoretische Physik, Universität zu Köln, Zùlpicher Str 77, 50937 Köln, Germany*

()

Abstract

Based on a perusal of available experimental data, we propose a possible explanation for the heavy-fermion Fermi liquid state coexisting with quasi-one dimensional antiferromagnetism in the low-carrier pnictide Yb_4As_3 . Both of these low temperature features are shown to originate from one single fact - the charge ordered state forming at high- T is imperfect, due to quantum fluctuations in the CO state. The quasi-1D magnetism is understood in terms of the physics of the squeezed Heisenberg chain, while the heavy fermion-like behavior arises from the compensation of the fraction of the Yb moments (which are disordered) by the $2p$ band of As . The proposed picture shows how the seemingly strange features observed experimentally can be reconciled as a result of this single hypothesis.

PACS numbers: 71.28+d,71.30+h,72.10-d

1. INTRODUCTION

Rare-earth pnictides like Yb_4As_3 have been increasingly studied in the past few years, as they are thought of as being "low-carrier density Kondo systems". Transport measurements show similarities with typical heavy fermion Fermi liquid metals [1], while the thermodynamics and the magnetic response [2] is characteristic of one-dimensional spin systems. A naive estimation of the carrier number from the Hall data leads one to conclude that the carrier density is very low [3]. How such a supposedly small carrier density can screen the Yb local moments to give a heavy FL at low- T is the issue central to the understanding of this material. Purely on theoretical grounds, one might want to ask:

(1) Under what conditions can a heavy-fermion like FL metal coexist with quasi-1D spin fluctuations? How do these degrees of freedom affect each other at low- T ?

(2) A more general, but related question: Are there hitherto unknown routes to heavy fermion behavior, other than the well-studied Kondo effect?

In this letter, we want to propose a route which ties together the various seemingly irrevocable facts that are known about this material. We start with a brief recapitulation of known experimental and theoretical facts, and then go on to show how both the heavy-fermion like transport and the lower- dimensional magnetism arise naturally from *imperfect* nature of the charge ordering that occurs at higher T . Our analysis also provides a natural explanation of the fact that the closely related materials Yb_4X_3 , $X = P, Sb$, behave very differently from Yb_4As_3 . The phosphide is an insulator all the way down to the lowest T , with a more perfect charge order, while the antimonide is a mixed-valence metal (no charge ordering) down to the lowest T .

Yb_4As_3 is a semiconductor at room temperature, with the rare-earth f -ion of Yb in a mixed valence state ($Yb^{14+} - Yb^{13+}$). At about 293 K, a collective JT distortion causes three of the four identical diagonals along the cubic cell to elongate, leading to a contraction of the fourth diagonal, into which the Yb^{13+} ions gather. Since Yb^{13+} carries a spin $1/2$, one has an (almost half-filled) chain with strong electronic correlations. These are precisely the degrees of freedom giving rise to the 1D spin fluctuations observed in inelastic neutron

scattering, and to the spin susceptibility and the γ coefficient of the specific heat, as shown on [2], and discussed on experimental [2] and theoretical grounds [3].

Since the spin degrees of freedom are those of the 1D Hubbard model, the spin excitations are fermionic spinons rather than conventional bosonic spin waves. But this is not all, as bandstructure calculations reveal that the carriers seem to come predominantly from the *As* 2p-band. A consistent picture of the low- T transport must necessarily involve the scattering of these carriers on the spin fluctuations of the Hubbard chain. If the chains were half-filled, leaving the *As* p carriers out of the reasoning would lead one to conclude that the material must be a Mott-Hubbard insulator. On the other hand, if one does include the *As* carriers, a heavy fermion-like resistivity can only result from the scattering of these light carriers off almost localized *Yb* 4f-spins. The issue then is whether this scattering (details have not been worked out) can give rise to a quadratic (in T) scattering rate. The large A value suggests strong scattering, but in view of the fact that one is dealing with spinon-pair fluctuations that scatter the light carriers, a concrete calculation is needed to answer the question. We argue, however, (see below) that this mechanism is *not* responsible for the observed resistivity, which, we show, has a more conventional interpretation.

This is intimately related to the second question posed above: the scattering giving rise to a HF-FL metal at low- T must necessarily involve quenching the local moment degree of freedom of the Hubbard chain. So one might want to address the question of a Kondo-like effect originating in a way different from the usual accepted one. The basic question should then be rephrased as:

Can light electron-like carriers scattering on spinon-pair fluctuations yield heavy fermion like behavior?

or,

Is the above view incorrect, and could a conventional Kondo effect occur as a result of scattering of the p -holes off the spin fluctuations of the fraction of the localized spins in the other three chains?

If the second point of view indeed holds, a consistent explanation for the above anomalous

features can indeed be given without having to take recourse to exotic scenarios.

To be able to decide the issue, one has to appeal to experiment. The experimental results need to be correlated and a common thread connecting the observed phenomena needs to be searched. We summarize the experimental results below.

(1) The high- T phase is a mixed-valent metal. This undergoes a first-order charge-ordering transition at $T_c = 293\text{K}$ via a collective band-JT effect. The effect is to shorten one of the four equivalent chains (at high T) and to elongate the other three. The f -holes carrying a spin $S = 1/2$ sit on the shorter chains, and because the Hubbard $U_{ff} \gg t_f$, the effective $f-f$ hopping strength, one has to deal with a strongly correlated 1D Hubbard like chain. But this is not the whole story, because bandstructure calculations have shown that the carriers responsible for conduction are in fact derived from the As 2p-band (which is a wide band, giving rise to small effective-mass carriers). The low- T heavy fermion behavior has to do with the scattering of the light p -holes off the almost localized f -moments of the Yb . The question for theory is: How can this give rise to a resistivity, $\rho(T) \simeq AT^2$ with large A ?

(2) The specific heat shows a *linear* T -dependence, and one might naively associate this as one of the signatures of usual heavy-fermion behavior especially since the ratio A/γ^2 is also characteristic of heavy fermion metals. What gives the game away is that a related material, Yb_4P_3 , an insulator, also has the linear term, with a γ -coefficient larger than that for Yb_4As_3 ! Thus, the linear specific heat can only result from the spin degrees of freedom, spinons, of the 1D Hubbard model. That this is indeed the case is shown conclusively by inelastic neutron scattering data, which reveals a spin dispersion which is almost that of an ideal 1D $S = 1/2$ AFM chain. An external magnetic field has been shown to result in significant changes in the γ coefficient, as well as in the spin susceptibility, while leaving the resistivity almost unchanged! Exactly the opposite happens with the effect of external pressure, as we discuss below.

First, we summarize the effect of an external magnetic field. A uniform longitudinal field has been shown to generate a staggered transverse field component along the x -direction,

resulting in the effective model given by

$$H_{ch} = 2I \sum_i \mathbf{S}_i \cdot \mathbf{S}_{i+1} - h \sum_i (-1)^i S_i^x - H \sum_i S_i^z \quad (1)$$

Calculation of the specific heat, $C(T)$, shows the opening up of a gap at low T in good agreement with experimental observations [4]. The static magnetic susceptibility depends on the orientation of the external field relative to the spin chain. What is so surprising is that this change in the spin excitation spectrum has very little influence on the low- T resistivity. This is hard to understand if the 1D spin excitations are assumed to drive the observed Fermi liquid resistivity.

Application of hydrostatic pressure has exactly the reverse effect: the resistivity changes drastically as pressure is increased, the main features being the suppression of the high- T "charge ordering" transition, a gradual but strong reduction of the broad maximum in $\rho(T)$, and a drastic decrease in the coefficient A . The suppression of the high- T CO state can be understood in terms of the increased hybridization between the As p and the Yb $4f$ orbitals. The specific heat and spin susceptibility, however, are completely unaffected by pressure.

Replacement of As by an ion like P should stabilize the charge ordered (CO) state. This is indeed observed [5], but with a larger γ coefficient of the specific heat than in Yb_4As_3 . The resistivity in this case is *insulating* all the way down to low T , confirming that the HF-FL behavior in Yb_4As_3 is *not* related to scattering off the 1D spinons, but is connected with the imperfect CO state in Yb_4As_3 . Experimental estimates [6] point to the disordering of the CO state with a small fraction of the Yb^{3+} on the three longer chains. This observation is further supported by LDA+U calculations [6], which show that the hopping integral *between* the short chain and the longer chains is *greater* than the intrachain hopping integral in the short chain. These $S = 1/2$ spins are randomly distributed in the three-dimensional host, and scatter the light As holes.

In this paper, we propose that both, (i) the one-dimensional magnetism, and (ii) the low- T heavy-fermion FL metallic phase observed in Yb_4As_3 result from one single phenomenon: the incomplete nature of the CO state, which sets in as a first-order transition

at $T \simeq 293\text{K}$ [1]. This high- T CO state has been sought to be explained by a collective band Jahn-Teller distortion [7,8], whereby the homogeneous mixed-valent state with non-integral Yb valence state of 2.25 is unstable to a state where the Yb^{3+} ($S = 1/2$) congregate predominantly on one chain. This chain is shortened, while the other three are elongated. However, this CO is not perfect and estimates as well as an explicit calculation of a Hubbard model with the Jahn-Teller distortions in the geometry of four interpenetrating chains relevant to Yb_4As_3 [6] show that a small fraction of the Yb^{3+} sites are on the other chains, an observation that is reconcilable with the fact that the hopping integral between the short and the long chains is greater than that along the short chain. This observation is crucial for the picture we propose below.

The 1D magnetism observed in this material is then understood in terms of the physics of the 1D Hubbard (or squeezed Heisenberg model [9]) chain. As is known [10], the spectrum of the 1D Hubbard model is characterized by spin-charge separation. The spin is carried by neutral fermionic excitations, i.e, by the spinons, while the charge degrees of freedom are described by spinless, hard core bosons, the holons. Because of spin-charge separation, one can continue using the Heisenberg model (with an exchange coupling that depends on the deviation from half-filling) to describe the spin dynamics [11].

We have computed the uniform static spin susceptibility and the specific heat from the thermodynamic Bethe ansatz (TBA) equations [12] for a modified Heisenberg chain with an exchange strength (dependent on the hole concentration) given by

$$I_{eff}(n) = n[1 - \sin(2\pi n)/2\pi n] \quad (2)$$

We point out that such an approach has also been used by Zvyagin [17] in the context of Yb_4As_3 . However, while we agree with [17] on the issue of the quasi-one dimensional magnetism in Yb_4As_3 , we differ on the origin of the FL-like resistivity (see below). The Hamiltonian is,

$$H_{ch} = 2I_{eff}(n) \sum_i \mathbf{S}_i \cdot \mathbf{S}_{i+1} \quad (3)$$

It is well known that the 1D Heisenberg spin model is completely integrable, and that the TBA gives an exact expression for the free energy of the system. Using the spinon formulation of the TBA (using the quantum transfer matrix) [12] the problem reduces to the solution of two coupled nonlinear integral equations.

$$\begin{aligned}\ln \mathfrak{a}(x) &= -\frac{\pi I_{eff}}{T \cosh x} + (k * \ln \mathfrak{A})(x) - (k * \ln \overline{\mathfrak{A}})(x - i\pi + i\epsilon), \\ \ln \overline{\mathfrak{a}}(x) &= -\frac{\pi I_{eff}}{T \cosh x} + (k * \ln \overline{\mathfrak{A}})(x) - (k * \ln \mathfrak{A})(x + i\pi - i\epsilon), \\ \mathfrak{A}(x) &= 1 + \mathfrak{a}(x), \quad \overline{\mathfrak{A}}(x) = 1 + \overline{\mathfrak{a}}(x).\end{aligned}\tag{4}$$

$$k(x) := \frac{1}{2\pi} \int_0^\infty \frac{e^{-\frac{\pi}{2}k}}{2 \cosh \frac{\pi}{2}k} \cos(kx) dk,\tag{5}$$

where the asterik denotes convolution $(f * g)(x) := \int_{-\infty}^\infty f(x-y)g(y)dx$. The free energy is given by $f(0)$ with

$$f(x) = -T \int \frac{\ln[\mathfrak{A}(y)\overline{\mathfrak{A}}(y)]}{\cosh(x-y)} dy,\tag{6}$$

ignoring the contribution of the groundstate energy. Solving these equations by the fast-fourier transform method, we have computed the spin susceptibility and the specific heat as a function of T for the case applicable to Yb_4As_3 , i.e, with a small fraction of spins in the other three chains ($n = 0.9$). Calculation of the staggered spin susceptibility has already been carried out in [4], and is consistent with a gapped spin-wave spectrum resulting from a field-induced anisotropy.

The calculated curves are in fair agreement with the experimental results for this material. In this context, it is worthy of mention that the effect of static disorder induced by the vacancies (absent spins) on the shorter chain may become important at very low T [13]. This effect is absent in the above calculation.

To account for disorder, we use the results in [16] where an arbitrary distribution of impurities (which do not destroy the integrability) parametrized by the real numbers θ_j at the site j on the spin chain, are added to a Heisenberg spin chain. This approach has been applied by Zvyagin [17] for the same purpose in the case of Yb_4As_3 recently. The total free

energy of the spin chain with impurities is $F = L^{-1} \sum_j f(\frac{\pi}{2}\theta_j)$ where the sum is taken over all the sites (for sites without impurities we take $\theta_j = 0$), and $f(\theta_j)$ is given in (6). Now an appropriate random distribution of values θ_j , $P(\theta_j) \propto \exp(-\pi(\lambda - 1)|\theta_j|)$ can be taken resulting in a power law divergence of the susceptibility at very low temperatures and the linear coefficient of the specific heat γ

$$\langle \chi \rangle \propto \langle \gamma \rangle \sim T^{\lambda-1},$$

taken $\lambda \sim 0.26-0.42$ coincide with data on real disordered quasi 1D spin $\frac{1}{2}$ AF systems. This is quite consistent with the observed power-law divergence in $\langle \chi \rangle$. It would be interesting to see whether $\langle \gamma \rangle$ also shows a similar divergence at very low T .

The specific heat shows the linear low- T contribution. A comparison of the curves for two values of n shows that the γ coefficient of the linear term increases as n increases towards unity, providing a simple explanation for the larger γ value for Yb_4P_3 compared to Yb_4As_3 . The specific heat in an external magnetic field has been studied [4] by mapping the spin model in a staggered transverse field (induced by the uniform longitudinal field) onto a sine-Gordon model, and accounts naturally for the field-induced opening up of the gap in this material. Thus, the magnetic fluctuations are well understood in terms of the excitation spectrum of the 1D Heisenberg model, as was inferred previously [1-4].

To understand the origin of the Fermi liquid characteristics in transport, we observe that the small fraction of the localized spins in the three elongated chains can be modeled by an Anderson-like model with large U (since the Yb holes in the other three chains do not order). The Hamiltonian is then given by,

$$H = \sum_{k\sigma} C_{k\sigma}^\dagger C_{k\sigma} + \sum_{ik\sigma} t_k (f_{i\sigma}^\dagger C_{k\sigma} + h.c) + \sum_i U n_{if\uparrow} n_{if\downarrow} + \sum_{i\sigma} (\mu n_{ic\sigma} + E_f n_{if\sigma}) \quad (7)$$

where the $f_{i\sigma}, f_{i\sigma}^\dagger$ represent the Yb 4f fermions localized on the longer chains. In this case, we use the approach developed in [14] to compute the local spectral density and the resistivity in $d = \infty$. In this case, our effective Anderson model yields a correlated Fermi liquid metallic state off half-filling (which is applicable to Yb_4As_3 , with $n_f \simeq 0.1$). The actual

lattice coherence scale, T_{coh} , can be vastly different from the single-impurity Kondo scale, T_K [14]; The c -fermion selfenergy can be computed from the $d = \infty$ approach [15]; in the low- T regime, it takes on the simple form,

$$Im\Sigma_c(\omega) = \frac{(U)^2}{D^3}[\omega^2 + \pi^2 T^2]x(1-x) \quad (8)$$

where D is the free bandwidth of the As ($2p$ band(s)) and $x = n_f$. This immediately tells us that the resistivity follows the T^2 law characteristic of FL behavior. The coefficient of the T^2 term is given by $A = \frac{(U)^2}{D^3}$ and is large for $U \gg D$. Notice that external pressure would increase D , reducing the coefficient A , as indeed observed.

One might wonder why the shorter chain that gives rise to the observed 1D magnetism does not seem to affect the transport properties. To see how this can come about, recall that in the spin-charge separation scenario, the holon and spinon velocities are $v_h \simeq xt_f$ and $v_s \simeq I_{eff}$. These are much smaller than the Fermi velocity of the $2p$ carriers, as deduced from the bandstructure calculation [6]. Given that $v_F \gg v_h, v_s$, the scattering process involving the $2p$ hole and a spinon or a holon is unfavorable from the viewpoint of energetics (this process would dominate if $v_s < v_F < v_h$). Thus the heavy fermion FL characteristics involves, in our picture, the scattering of the light $2p$ holes off the (almost localized on the time scale of the p fermion hopping) localized f spins on the other three chains in Yb_4As_3 . In this context, we mention that it has been proposed in [17] that scattering of the As p holes off the spinon excitations of the squeezed spin chain gives a resistivity going like T^2 . If this were indeed true, one would expect the T -dependence of the resistivity to change upon the application of an external magnetic field (which induces a spin gap) in contradiction with experimental evidence. The small magnitude of the magnetoresistance and the $\rho(T, H) \simeq A(H)T^2$ behavior seen experimentally is thus in contradiction to the proposal in [17], but is completely consistent with the mechanism proposed here. In any case, it is highly improbable that scattering of light fermions off the spinons (holons) could yield such a large T^2 term in the resistivity.

If the picture proposed above is correct, a more perfect charge ordering of the Yb f holes

along chains should disfavor the onset of heavy fermion FL formation. This connection is indeed borne out by experiments on Yb_4P_3 where a more perfect CO state is accompanied by insulating behavior with a larger γ co-efficient. The more perfect CO state is a signature of decreased effective $f - d - p$ hybridization, a corresponding decrease in the tendency to itinerance, and is consistent with the insulating resistivity observed for this material. A more perfect CO state also increases the number of spins on the shorter chain, and the higher γ -coefficient is easily understood as arising from the spinon excitations of the squeezed Heisenberg chain, as shown before.

In conclusion, we have proposed that the apparently strange features in the low- T metallic state in Yb_4As_3 , i.e, a heavy fermion metal coexisting with 1D quantum antiferromagnetism, are readily understood to arise from a single observation: the charge-order arising at higher T is not complete, and a small fraction of the $S = 1/2$ moments on Yb reside on the three longer chains. The 1D antiferromagnetism is naturally understood in terms of the squeezed Heisenberg chain, while the heavy fermion FL properties at low- T result from the compensation of the Yb moments on the other three chains (the problem can be treated as three-dimensional) by the low density of carriers (coming from the As 2p bands).

Acknowledgments J.R.R.M. wants to thank Prof. A. Klümper for discussions and for kindly making available his computer routines. M. S. Laad wishes to thank Prof. P. Fulde for many discussions related to Yb_4As_3 and to Prof. Müller-Hartmann for a fruitful discussion.

References.

- [1] A. Ochiai *et al.*; J. Phys. Soc. Japan. **59**, 4129 (1990).
- [2] M. Kohgi *et al.*; Phys. Rev. **B56**, R11388 (1997).
- [3] P. Fulde *et al.*; Europhys. Lett. **31**, 323 (1995).
- [4] see, for example, S. Takagi *et al.*; Physica B **281-282**, 462 (2000) and references therein.
- [5] M. Oshikawa *et al.*; J. Phys. Soc. Jpn. **68**, 3181 (1999).
- [6] for the experimental evidence, see K. Iwasa *et al.*; Physica B **281-282**, 460 (2000),

and references therein. For the results of the LDA calculation, see V. Antonov *et al.*, Phys. Rev. B **58**, 9752 (1998).

[7] P. Fulde *et al.*; Europhys. Lett. **31**, 323 (1995).

[8] Y. M. Li *et al.*; Phys. Rev. Lett. **78**, 3386 (1997).

[9] H. Shiba, Phys. Rev. B **6**, 3, 930 (1972).

[10] for a detailed exposition of these ideas, see, N. Andrei, in "Lecture Notes of the Trieste Workshop on Integrable Field Theories", ICTP, Trieste (1994).

[11] these ideas become formally exact as $U \rightarrow \infty$, where the total wave-function can be expressed as a direct product of a spinless fermion and a squeezed Heisenberg part.

[12] A. Klümper *et al.*; Phys. Rev. Lett. **84**, 4701 (2000), Eur. Phys. J. **B 5**, 677 (1998).

[13] F. Steglich *et al.*, Z. Phys. B: Condens. Matter. **103**, 235 (1997).

[14] A. Georges *et al.*; Revs. Mod. Phys. **68**, 13 (1996).

[15] the c-fermion self-energy of this form follows from second order perturbation theory, but in fact is already close to the actual lattice self-energy in $d = \infty$.

[16] A. Klümper and A. A. Zvyagin, Phys. Rev. Lett. **81**, 4975 (1998); A. A. Zvyagin, Phys. Rev. B **62**, 6069 (2000).

[17] A. A. Zvyagin, Phys. Rev. B **62**, 12175 (2000).

FIGURE CAPTIONS.

FIGURES




FIG. 1. Magnetic susceptibility χ at low temperature T for the spin $S = 1/2$ antiferromagnetic uniform Heisenberg chain of length N .




FIG. 2. Electronic specific heat C versus temperature T for the $S = 1/2$ AF uniform Heisenberg chain.